



Sample mortar mix for Witten Fell Stone from Yorkshire Stone gate pillars. Mortar mix = 1 part Hanson NHL 3.5 hydraulic Lime 3 parts coarse sand from Borrass quarry.





Sample mortar mix for repair of stone front walls and for flanking walls.
Mortar mix = 1 part Hanson NHL 3.5 hydraulic Lime 3 parts coarse sand
from Borrás quarry.

